

# Dimensional Stability Test Certificate

Monday August 31<sup>st</sup>, 2020

Terra Mater Hardwood Floors Pty Ltd (PO BOX 4540 Dandenong South VIC 3175)

Sample Description: SPC Vinyl Plank

Date Tested: August 2020 (Tested through FORAY Laboratories - NATA Accreditation 1231)

Test Method: ISO 2551-1990 "Machine-made textile floor coverings – Determination of dimensional changes due to the effects of varied water and heat conditions".

Test Results:

Mean Linear change when exposed to:	SPC Vinyl Plank	Australian Carpet Classification Scheme requirements
Heat at 60°C for 2 hours	Length: -0.10% Width: -0.10%	Length: ±0.2% Width: ±0.2%
Water at 20°C for 2 hours	Length: -0.05% Width: -0.05%	Length: ±0.2% Width: ±0.2%
Heat at 60°C for 24 hours	Length: -0.15% Width: -0.15%	Length: ±0.2% Width: ±0.2%
Standard atmosphere for 48 hours	Length: -0.05% Width: -0.00%	Length: ±0.2% Width: ±0.2%
Degree of cockling observed	None	None
Negative sign denotes shrinkage		



Dr. Vyt Garnys  
PhD, BSc(Hons) AIMM, ARACI, ISIAQ  
ACA, AIRAH, FMA  
Managing Director and Principal Consultant



Tuan Duong  
BEng(Chemical Engineer)  
Consultant



Travis Hale  
BSc (Biotechnology)  
Consultant

V2008018